

SPORTFLOOR GRIP

TWO-COMPONENT WATER-BASED SEALER FOR PREFINISHED SPORTIVE FLOORS

Two-component adhesion promoter sealer, suitable as first coat on big prefinished surfaces. It improves the grip of the successive coats of varnish or paints from Sportfloor range and guarantees a perfect adhesion.

Sportfloor Grip is easy to apply, it keeps the original color of the wood and it has got low VOC content.



Technical data

Physical characteristics (20°C – 60% R.H.)			
Specific gravity of the blend	1,030 kg/l		
Ratio & times (20°C – 60% R.H.)			
Mixing ratio	10:1	Light walking	1h
Pot life	4 h (see note)	Overcoat	At least 4 hours
Technical characteristics			
Yield	14-16 m ² /lt	Maximum VOC content limit values for the specific category from Eu.Dir.42/2004	Cat.A/j (WB): 140 g/l (Jan. 2010)
Dilution	10-15% water		
Application temperature	> 10 °C	VOC content pure product	< 140 g/l
Storage & Labeling			
Storage of original unopened packaging at ambient temp.	12 months Protect from freeze	Symbols of risk	NONE
Tools cleaning	Clean the roller immediately after use with water and Additivo S/43. Rinse with clean water and store it into Soluzione di Lavaggio S27.		
Packaging	Comp. A: 5 lt can	Comp. B: 0,5 lt bottle	

Application

Preparation of the surface and mixing.

The prefinished surface must be dry, clean and free from residue of waxes of other maintenance products. If necessary wash the floor with the wax remover Nettar 2 diluted ~1:20 with water.

The whole surface of the prefinished floor must be homogeneously sanded with a new net (grit 180-220) and the dust must be completely removed.

Shake well A component; slowly pour B component into the A component while mixing (respect the correct ratio 10:1).

Application and overcoating.

Apply one coat of Sportfloor Grip with a proper roller (hair 4-6 mm) or a brush, taking care to treat in a uniform way the whole surface; to get best results, the coat must be very thin.

After at least 4 hours, the floor is ready for overcoating with Sportfloor Finish varnish or Sportfloor Color, Tover specific paints for lines and areas.

Notes

- ✓ Even if the blend remains liquid for few hours, it is better to apply it within the pot life of 4 hours to obtain a homogeneous film.
- ✓ The efficiency of Sportfloor Grip as an adhesion promoter has been tested on a large scale on prefinished floors; anyway it is always recommended to previously check the adhesion of the complete coating cycle, due to the high diversity of industrial finishing treatments on the market. It is better to wait for at least one week in order to have the final adhesion result.



TOVER S.R.L.
Via Rosa Luxembourg 2/A
10093 COLLEGNO (TO)
P.IVA 07783540011
R.E.A. n°920259
Tel.: +39-011/7792823
Fax: +39-011/7792749
www.tover.com
e-mail: info@tover.com
Made in Italy



Safety rules

FOR PROFESSIONAL USE ONLY. Strictly respect the information reported on labels and consult safety data sheets before use.

Disposing of waste

Dispose not used product and empty containers in accordance of local in force regulations.



TOVER S.R.L.
Via Rosa Luxembourg 2/A
10093 COLLEGNO (TO)
P.IVA 07783540011
R.E.A. n°920259
Tel.: +39-011/7792823
Fax: +39-011/7792749
www.tover.com
e-mail: info@tover.com

Made in Italy



WARNING: The information reported in present technical data sheet are for guidance only and they do not hold our responsibility; the environmental conditions and the employ modalities are out of our control. We advice to check that the product fits for the work to be done.

REV.1 28-03-2011. Current Technical Data Sheet replaces the previous one.