ATTIVATORE

PRE-TREATMENT TO ENHANCE THE EFFECT OF FOSSIL

Natural oxidizing agent in water emulsion, specific to treat wood before the application of Fossil ageing product.

The product is colourless and odourless; it is particularly efficient on oak, larch and other species rich of tannin. The application of Attivatore before a treatment made with Fossil gives the wood a darker and more intense final aspect.





P	hysical characterist	tics (20°C – 60% R.H.)	
Specific gravity	1,0	pH pure product	3
	Ratio & times (2	20°C – 60% R.H.)	
Dilution	Water – no limit	Over-application Fossil	1-2 hours
	Technical cha	aracteristics	
Yield	5-7 m ² /l (see notes)	Application temperature	> 10 °C
	Storage &	Labelling	
Storage in original closed packing at T>10 °C	12 months Protect from freeze	Symbols of risk	None
Tools cleaning	Immediately after use with water		
Packaging	1 and 5 litre]	
	Appli	ication ——	

Technical data

Support preparation

The wood to be treated must be unfinished. If there is a previous treatment (lacquer or oil), remove any residue.

Complete the sanding procedure with an abrasive paper with a grit less than 100 to enable an optimum impregnation.

The surface can be smooth or brushed; a brushed wood will valorise the final effect of the reactive ageing products.

Application

Apply **Attivatore** with a brush, a roller, by spray or with Mini-Tunnel machine; the application must be homogeneous and the wood must be wet. The product can be applied pure or diluted with water; the more diluted, the lowest will be its darkening intensity of Fossil.

It is thus better to make to test the get the requested aspect.

Leave Attivatore dry for 1-2 hours and apply Fossil. Sanding is not compulsory.

N.B. used alone, once dry, Attivatore does not create any colour change. The final result will be obtained only with the application of Fossil.

Note

- ✓ Attivatore has no real effect if used with other oxidizing agents like Bosch Vej, Bosch Ciair or Bosch Gris
- ✓ **Attivatore** is efficient only on wooden species rich of tannin.
- ✓ The final aspect of the treated wood with any reactive agent is directly conditioned by the wood "answer". That is why some very different chromatic effect may appear. It is better to make preliminary tests.
- ✓ The product yield is only an indication as the absorption level of the wood is much variable, the dilution is also an important factor together with the application tool.



TOVER S.R.L. Via Rosa Luxembourg 2/A 10093 COLLEGNO (TO) P.IVA 07783540011 R.E.A. n°920259 Tel.: +39-011/7792823 Fax: +39-011/7792749 www.tover.com e-mail: info@tover.com



SFC - 42

✓ Avoid product stagnation on the surface.

Safety rules

FOR PROFESSIONAL USE ONLY. Strictly respect the information reported on the labels and consult safety data sheets before use. Even if the product has no symbol of risk, it is recommended to use gloves and protective cloths.

Disposing of waste

Dispose not used product and empty containers in accordance of local in force regulations.







The information reported in present technical data sheet are for guidance only and they do not hold our responsibility. Adapt the use of our products to the environmental conditions and materials to be treated. *REV.1 25-09-2013* Current Technical Data Sheet replaces the previous one.