

# Durolak DD 60

Two-component polyurethane lacquer – Semi glossy



Varnishes & Finishing

Durolak DD 60 is a solvent-based high solid lacquer with a low VOC content. Having high coverage properties, it enables to achieve flawless finishes in only two coats. The film on the surface has a very good resistance to abrasion and excellent physical-chemical and self-levelling performance. The lacquer is also particularly easy to apply.

## Durolak DD60

### Technical data at 20 °C – 60% R.H.

Aspect	Component A – Opalescent liquid Component B – Transparent liquid
Mixing ratio	1:1 in volume
Mixture density	1,020 kg/litre
Dust dry	30 minutes
Touch dry	5 – 7 hours
Sanding	24 hours
Mixture pot-life	4 hours
Gloss 60°	60 gloss
Resistance to abrasion after 7 days	25 mg Taber Abraser, CS10 wheels, 1000g 1000 revolutions
Yield	10 – 12 m <sup>2</sup> /litre
VOC	< 500 g/litre, cat A/j (BS), limit 500 g/litre (2004/42/CE)
Application temperature	From +10 to +35 °C
Tools cleaning	Immediately after use with Solvente di Lavaggio S 23.
Storage	12 months in original sealed package
Packaging	Drums of 5 + 5 litres



### Certifications

### Application

Sand the wood floor to completely remove any previous lacquer and any trace of oils, grease and wax. Fill the cracks by mixing wood dust with Legastucco RS 20 or Legastucco RS A and complete the sanding cycle with a 120 - 150 grit abrasive. Thoroughly clean the surface. Apply a coat of the two-component solvent-based sealer Gran Fondo NP with a roller or brush and let it dry for about 8 hours. Sand with 150 grit sandpaper. Apply the finishing as described below:

Shake component A well, mix with component B in the exact use ratio (1: 1) and let the mixture react for 10 minutes. Apply a coat of lacquer with a brush or roller. The Gran Fondo NP + Durolak DD 60 two-coat cycle guarantees a full and homogeneous finishing.

### Notes

After the two-coat Gran Fondo NP + Durolak DD 60 cycle, if a second coat of lacquer is required, wait at least 24 hours and sand using a fine-grained sandpaper (220); apply the lacquer within 7 days.

The actual gloss value of the lacquer film is reached after about 3 days.

### Maintenance

For the cleaning and frequent maintenance of floors lacquered with Durolak DD 60, we recommend the use of a neutral detergent like Pulito Parquet or a sanitizing one like Saniparquet. For extraordinary maintenance, we recommend the Lux polish.

### Safety regulations

PROFESSIONAL USE PRODUCT. Strictly comply with what is stated on the label and consult the safety data sheet before using the product.

### Disposal

Dispose of the unused product and empty packaging in accordance with the provisions of the local legislation in force

The information reported in the present technical data sheet are for guidance only and they do not hold our responsibility. Adapt the use of our products to the environmental conditions and materials to be treated.

Rev 03 – 13/05/2020  
Current Technical Data Sheet replaces the previous one.